

DECORATIVE PAINT

G2 Interior Semi-Gloss Acrylic Paint

Emulsion Paint

water-base

Textured ^AAcrylic Coating

GoMix®



G2 INTERIOR SEMI-GLOSS ACRYLIC PAINT

An acrylic blended latex semi-gloss coating designed for application to a wide variety of interior surfaces. Form a highly durable, washable finish with excellent hiding.

FEATURES

- Ideal for trim, cabinets, doors, and wall surfaces that require frequent cleaning
- Excellent durability
- Spatter resistant
- Easy to touch up
- Soap & water clean up
- Dries to a uniform semi-gloss finish
- Self Priming on most surfaces
- Excellent flow and leveling
- Low odor and low VOC even after tinting

RECOMMENDED FOR

- Ideal for interior trim, doors, cabinets, walls, and ceilings.
- For new or previously painted wallboard, masonry, and primed or previously painted plaster, and wood.

SURFACE PREPARATION

- Surfaces to be painted must be clean, dry, and free of dirt, dust, grease, oil, soap, wax, scaling paint, water soluble materials and mildew.
- Remove any peeling or scaling paint, and sand these areas to feather edges smooth with adjacent surfaces.
- Glossy areas should be dulled. Drywall surfaces must be free of sanding dust. Prime spot before and after filling nail holes, cracks, and other surface imperfections.
- New plaster or masonry surfaces must be allowed to cure (30 days) before applying base coat. Cured plaster should be hard, have a slight sheen and maximum pH of 10; soft, porous or powdery plaster indicates improper cure.
- Never sand a plaster surface; knife off any

protrusions and prime plaster before and after applying patching compound.

- Poured or pre-cast concrete with a very smooth surface should be etched or abraded to promote adhesion, after removing all form release agents and curing compounds.
- Remove any powder or loose particles.

Difficult Substrates:

- Gomix Co., Ltd offers a variety of specialty primers for use over difficult substrates such as bleeding woods, grease stains, crayon markings, hard glossy surfaces, galvanized metal or other substrates where paint adhesion or stain suppression is a particular problem.
- Your Gomix ® retailer can recommend the right problem-solving primer for your special needs.

WARNING!

If you scrape sand or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a respirator to control lead exposure. Carefully clean up with a HEPA vacuum and a wet mop.



PRIMER/FINISH SYSTEM

- Gomix® Interior Semi-Gloss Acrylic Paint is self priming on most surfaces.
- Gomix® Interior Semi-Gloss Acrylic Paint will act as its own primer, providing the optimal foundation for the subsequent finish coat.
- On bare substrates two coats are required; previously painted surfaces can be finished with 1 or 2 coats.
- While the high quality of our products sometimes makes one-coat coverage achievable, Gomix recommends two coats of this product to achieve full color development and to maximize paint film performance.

Wood, and engineered wood products:

Primer: Gomix® S3 Interior Latex Primer & Sealer

Finish: 2 coats of Gomix® Interior Semi-Gloss Acrylic Paint

Drywall:

Finish: 2 coats of Gomix® Interior Semi-Gloss Acrylic Paint

Plaster:

Primer: 1 coat of S3 Interior Latex Primer & Sealer

Finish: 2 coats of Interior Semi-Gloss Acrylic Paint

Masonry, Rough or Pitted:

Primer: GM11 Interior Acrylic Putty

Finish: 2 coats of Interior Semi-Gloss Acrylic Paint

Masonry, Priming Smooth Poured or Precast Concrete:

Primer/Finish: 2 coats of Interior Semi-Gloss Acrylic Paint

APPLICATION

- Use Gomix® Interior Semi-Gloss Acrylic Paint when the surface and air temperatures are between 50-90°F (10-32°C).
- Stir paint occasionally. Intermix containers of the same product to ensure color and sheen uniformity
- Use a high quality 3/8-1/2" nap roller cover, nylon/polyester brush or an airless sprayer (.015"-.019" spray tip, 60 mesh filter).

- Coverage is 23-27 m² per gallon depending on the surface texture, porosity and application method.
- Do not thin if using a roller or brush; however, thinning is required if using a sprayer, thin with water at a rate of no more than 1/2 pint per gallon.
- Certain colors may require more than one coat for complete hide.

DRY TIME

- Dries to touch in 2 hours at 77°F (25°C) and 50% humidity; re-coat in 4 hours.
- Longer dry time required in cooler temperatures and higher humidity.
- Darker colors may require longer dry time between coats.
- After 2-4 weeks, cured paint film could be cleaned with a mild, non-abrasive liquid detergent.
- Dry paint film is mildew resistant.

CLEAN UP & STORAGE

- Use soap and water.
- Properly dispose of all soiled rags and protect unused product from freezing.
- For disposal of unused paint products, please contact your household refuse collection service.

ENVIRONMENTAL, HEALTH&SAFETY INFORMATION

- Use only with adequate ventilation.
- Do not breathe spray mist or sanding dust.
- Ensure fresh air entry during application and drying.
- Avoid contacting with eyes and prolonged or repeated contacting with skin.
- Avoid exposure to dust and spray mist by wearing a respirator during application, sanding and cleaning up.
- Follow respirator manufacturer's directions for respirator use. Close container after each use.
- Wash tools thoroughly after handling.



TECHNICAL DATA SHEET

Technical Data	
Vehicle Type	Proprietary Acrylic Latex
Pigment Type	Titanium Dioxide
Solids Volume	39%
Coverage per Gallon at Recommended Film Thickness	23-27 m ²
Recommended Film Thickness (Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure color uniformity and minimize the disposal of excess paint)	<ul style="list-style-type: none">– Dry 1.2 mils– Wet 3.8 mils
Dry Time @ 77° F (25° C) @ 50% RH (Painted surfaces can be washed after two weeks. High humidity and cool temperatures will result in longer dry, recoat and service times)	<ul style="list-style-type: none">– To Touch 2 Hour– To Recoat 2 to 4 Hours
Dries By	Evaporation, Coalescence
Viscosity	87 ± 2 KU
Gloss / Sheen	Semi-Gloss (38-48 @ 60°)
Surface Temperature at Application	<ul style="list-style-type: none">– Min. 50° F (10°C)– Max 90° F (32°C)
Storage Temperature	<ul style="list-style-type: none">– Min. 40° F(5°C)– Max 100° F(38°C)
Volatile Organic Compounds (VOC)	42 Grams / Liter .35 LBS / Gallon
Weight Per Gallon	5.3kg

For further information consult our Technical Department

GoMix Co., Limited

Hong Kong Office: Bright Way Tower 33 Mong Kok Rd Mong Kok KL HK

Guangzhou Office: Rm 717-718, Huaerdun Hotel, #557, Xinti R, Baiyun, Guangzhou, China

Tel.: 0086 20 6106 9818

Email: hkgomix@gmail.com

Fax: 0086 20 6106 9819

Web.: <http://www.gomixcoat.com>